

IN THE APPLICATION OF:

ROGER MOONS

CASE

AD6883USNA

NO.:

APPLICATION NO.: 10/627902

GROUP ART UNIT: 1761

FILED: JULY 25, 2003

EXAMINER: DREW E. BECKER

CONFIRMATION NO.: 3469

FOR: IMPROVED THERMOPLASTIC POLYMERIC OVENWARE

Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450

DECLARATION UNDER 37 C.F.R. 1.132


- 1. I obtained a B.S. in Chemistry from the Polytechnic Institute of Brooklyn in 1962 and a Ph.D. in Organic Chemistry from the University of California at Davis in 1967.
- 2. I am currently receiving a pension from the assignee of this application E.I. DuPont de Nemours & Co., Inc. (hereinafter DuPont).
 - 3. I am a Registered Patent Agent (No. 33,852).
 - 4. I am currently a consultant for DuPont on technical and patent matters.
 - 5. While consulting for DuPont I directed an experiment as set forth below.
- 6. A composition containing 55 weight percent of Zenite® 6000 Liquid Crystalline Polymer (available from E. I. DuPont de Nemours & Co., Inc., Wilmington, DE 19998 USA), 37 weight percent talc, and 8 weight percent carbon fiber was prepared by melt mixing in a 30 mm Werner & Pfleiderer twin screw extruder. The techniques used to prepare this composition were similar to those commonly used to prepare other compositions containing LCPs.
- 7. The above composition was molded in a 6 oz. HPM injection molding machine into 4 inch diameter disks.

- 8. An above described disk (after machining) was tested for through plane thermal conductivity. The resulting value was 0.368 W/m°K.
- 9. The attached pages from Electronic Research Notebooks D100052 and D100008 describe this experiment and the conditions used for the various operations. The sample number for the above described composition was 13-1. The composition of sample 13-2 has been blanked out from the page, and the results for the thermal conductivity of this sample have been omitted.

el D. Citron

Date: May 2 2007

T:\Patent Documents\Eng. Polymers\AD-68xx\AD6883\AD6883 Declaration of Joel Citron.doc



Identification Number: D100052-28.01

Experiment Name : D100052-13

Program Name : Zenite

Project Name: Thermoconductivity for Joel Citron

Document Name : D100052-13 series Thermal Conductive Zenite Joel Citron.pdf

Site Name : EXP ST

Business Unit : Engineering Polymers

Author Name : Mike J. Molitor


Date: 02/26/2007 14:59:57

Co-Author Details :


Witness Name : Adcoc	k, Dave Date: 02/26/2007 15:03:04
Date (GMT)	Signed by
	Name: Mike J. Molitor
2/26/2007 07:59:57 PM	Pre-Sig Hash: 9b9c723fedbb8ec913753be9ae4abc415c4f0fal
Justification	By entering your password you verify that you planned and/or executed the work, directed the work, analyzed the result, or drew the conclusions described within this document.
	Name: Adcock, Dave
2/26/2007 08:03:05 PM	Pre-Sig Hash: 4004778267dalf14aed9d10dd217ba30817d5b91
Justification	By entering your password you will be signing to say that you have witnessed the information contained in this document
****	Name:
	Pre-Sig Hash:
Justification	·
	Name:
	Pre-Siq Hash:
Justification	
	Name:
	Pre-Sig Hash:
Justification	
	I Name
	Name: Pre-Sig Hash:
	FEE DEG MADE.
Justification	

Information in this report is proprietary and should be handled according to DuPont Information Security policies

13-1	13-2
55	
37	
8	
	55 37



BOOK	PAGE				de Nemo				DATE	· 10-	-30-o
E 1115	63- 3										200
JR NO. /275 FOR MUCE POLYMER TY MOLD 1/2 /	PE REA	46TE	52		DATE_/O- CHARGE/S SCREW_O NOZZLE_	BU_=-	<u> </u>	CYLIN RAM S SCREN BACK	PEED W SPE	<i>FA</i> :	7 33.54
SAMPLE NO.	REAR	CENTER	FRONT	NOZZLE	MOLD TEMP	CYI B !	PE H	PR(BOOST		MELT	SUR
	32'5	1			100 100			Τ	1		1



QPIN DuPont Electronic Laboratory Notebook

Identification Number: D100008 32.02

Experiment Name : D100008-18

Program Name : Zenite

Project Name: Thermal Conductivity

Document Name : ThermalConductivityofD100052-13-land13-2.pdf

Site Name : EXP ST

Business Unit : Engineering Polymers

Author Name : Adcock, Dave

Date: 02/26/2007 12:57:03

Co-Author Details :

Witness Mame : Harvo	Pata : 02/26/2007 13:07:04
Date (GMT)	Signed by
	Name - Addock, Dave
 2/26/2007 05-57-03 PM	
Justification	By entering your password you verify that you planned and/or executed the work, analyzed the result, or drew the conclusions described within this document.
	Name: Harvey, Pat A.
2/26/2007 06:07:04 PM	Pre-Sig Hash: 73b0cadeclbdedf8234bdc64d8lae2e30laf8lba
Rudeifacetace	By entering your password you will be signing to say that you have witnessed the information contained in this document
	Name:
ĺ	Pre-Sig Hash:
Justification	
	Name:
	Pre-Sig Hash:
Justification	
,	Name:
1	Pre-Sig Hash:
Justification	
	Name:
	Pre-Sig Hash:
Justification	

 Information in this report is proprietary and should be handled according to DuPont Information Security policies

USING TEST FILE : 13-1 LOS

The second secon

TEST DESCRIPTION 3100052-13-1

in action maided disc

SAMPLE ID : 13-1 SAMPLE THICKNESS: 3.030mm

Average sample temperature = 50 C Controller= 30 C

TU (C)	TG (C)	TL (C)	TH (C) TU-TL (C)	Q.	RATIO	
50.0	48.2	40.4	30:0 19:64	9472.1	0.211266	
60.6	48.0	40.8	29:5 19:75	10096.7	0.195657	
60.6	48.1	40.9	29:5 19:73	10107.1	0.195166	

Average sample temperature = 75 C Controller= 55 C

TU (C)	TG (C)	TL (C)	TH (C) T	U-TL (C)	Q	RATIO
78.1	65.9	58.4	49.3	19.74	8854.4	0.233231
85.2	72.0	65.6	54.7	19.63	10161.7	0.193207
85.2	72.0	65.6	54.7	19.62	10167.3	0.193013

USING CALIBRATION FILE: ESL04200.cal : 13-1.tst

USING FIRST ORDER FIT

USING TEST FILE

SAMPLE ID

SAMPLE THICKNESS

: 13-1 : 3.030mm

CTE


: 0.000e+000

THE SAMPLE HAS A THERMAL CONDUCTIVITY OF: 3.651347e-001 W/mK = 0.365
AND A THERMAL RESISTANCE OF B.298308e-003 m2K/W
AT A TEMPERATURE OF 50.78 C

: 19.73 C THE DELTA T THROUGH THE SAMPLE IS THE HEATER TEMPERATURE IS ; 29.54 C THE DELTA T ACROSS THE STACK IS : 31.10 C THE GUARD TEMPERATURE IS

0.370 W/ w.K THE EAMPLE HAS A THERMAL CONDUCTIVITY OF: 3.702624e-CO1 W/mK AND A THERMAL RESISTANCE OF : 8183385e-O03 m2K/W THE AT A TEMPERATURE OF : 75.40 C

THE DELTA T THROUGH THE SAMPLE IS : 18.62 C THE HEATER TEMPERATURE IS THE DELTA T ACROSS THE STACK IS : 54.65 C : 30.55 C : 72.02 C THE GUARD TEMPERATURE IS



Identification Number : D100052-28.01

Experiment Name : D100052-13

Program Name : Zenite

Project Name: Thermoconductivity for Joel Citron

Document Name : D100052-13 series Thermal Conductive Zenite Joel Citron.pdf

Site Name : EXP ST

Business Unit : Engineering Polymers

Author Name : Mike J. Molitor


Date: 02/26/2007 14:59:57

Co-Author Details :


Witness Name : Adcoc	k, Dave Date: 02/26/2007 15:03:04
Date (GMT)	Signed by
2/26/2007 07:59:57 PM	Name: Mike J. Molitor
2/26/2007 07:39:37 FM	Pre-Sig Hash: 9b9c723fedbb8ec913753be9ae4abc415c4f0fal
Justification	By entering your password you verify that you planned and/or executed the work, directed the work, analyzed the result, or drew the conclusions described within this document.
2/26/2007 08:03:05 PM	Name: Adcock, Dave Pre-Sig Hash: 4004778267dalf14aed9dl0dd217ba30817d5b91
	By entering your password you will be signing to say that you have
Justification	witnessed the information contained in this document
	Name:
	Pre-Sig Hash:
Justification	·
	Name:
	Pre-Sig Hash:
Justification	·
	Name:
	Pre-Sig Hash:
	rit big mon.
Justification	
	Name:
	Pre-Sig Hash:
Justification	·

Information in this report is proprietary and should be handled according to DuPont Information Security policies

Sample # D100052	13-1	13-2
Zenite 6000	55	•
Jetfil Talc 575C	37	
Carbon fiber Sigrafil	8	



IR NO 1275 NB NO D 10052 DATE 10 30 00 CYLINDER 6 UZ A FOR AULTED SCREW S.C.
FOR 400704 CHARGESBU 5.7. RAM SPEED FALT
POLYMER TYPE ZENUTE SCREW G.A. SCREW SPEED - MOLD & DOK (E-T) NOZZLE 4 7/9: BACK PRESS MAN.





DuPont Electronic Laboratory Notebook

Identification Number : D100052-28.01

Experiment Name : D100052-13

Program Name : Zenite

Project Name: Thermoconductivity for Joel Citron

Document Name : D100052-13 series Thermal Conductive Zenite Joel Citron.pdf

Site Name : EXP ST

Business Unit : Engineering Polymers

Author Name : Mike J. Molitor

Date: 02/26/2007 14:59:57

Co-Author Details :

Witness Name : Adcoc	ck, Dave Date: 02/26/2007 15:03:04
Date (GMT)	Signed by
2/26/2007 07:59:57 PM	Name: Mike J. Molitor
2/26/2007 07:59:57 FM	Pre-Sig Hash: 9b9c723fedbb8ec913753be9ae4abc415c4f0fal
Justification	By entering your password you verify that you planned and/or executed the work, directed the work, analyzed the result, or drew the conclusions described within this document.
<u> </u>	Name: Adcock, Dave
2/26/2007 08:03:05 PM	Pre-Sig Hash: 4004778267dalf14aed9d10dd217ba30817d5b91
Justification	By entering your password you will be signing to say that you have witnessed the information contained in this document
,	
	Name:
<u> </u>	Pre-Sig Hash:
Justification	
	Name:
	Pre-Sig Hash:
Justification	
ļ	Name:
	Pre-Sig Hash:
Justification	
	Name:
	Pre-Sig Hash:
Justification	


Information in this report is proprietary and should be handled according to DuPont Information Security policies

 Sample # D100052
 13-1
 13-2

 Zenite 6000
 55

 Jetfil Talc 575C
 37

 Carbon fiber Sigrafil
 8



BOOK	PAGE					urs and Com			
E 1115	33- 3	6 _{FUNDO}	6 0z	SOAL	TESTAV	e TOCOM	DA11	70.	30 %
JR NO. /275 FOR MUCTO POLYMER TYP MOLD 1/4 " A	E ZEA	14.75	S2		DATE/O- CHARGE/S SCREW_G NOZZLE	BU <u>E. /.</u>	CYLINDER_ RAM SPEED SCREW SPE BACK PRESS	FA:	7
SAMPLE NO.	REAR	CENTER	FRONT	NOZZLE	MOLD TEMP A B	CYCLE B I H	PRESS. ROOST: INJ	MELT	SUR RM
/3 - 2	32'6	352	332	323	140 100	2 /5 /5	350 250	1	36

13 - 2	325	332	332	323	100 100	2 /	5 15	350	250	363
	325	337	332	ن د ي	100	Z .	5 15	ىعد	250	ي يو
13-/	1 22					1	i	1	, 1	
					1	-		 		- A
		<u> </u>			1					
	T	1			:		-:-	-	$\dot{\bot}$	
		1				-		\vdash		
				Ī		 	1	+		
	<u></u>									7.0
									_	1
				•						423
										7.0
										428
	_								-	
										1 222
										/
, » ~ ~ ~ 600 25137121	~ K 10	- Lyn					ı,	Are /	0-30-06	
, y egadzentei WTNECSED 8Y	Je so.	Jan 1	7						0-30-06	

Identification Number : D100008 32.02

Experiment Name : D100008-18

Program Name : Zenite

Project Name: Thermal Conductivity

Document Name : ThermalConductivityofD100052-13-land13-2.pdf

Site Name : EXP ST

Business Unit : Engineering Polymers

Author Name : Adcock, Dave

Date: 02/26/2007 12:57:03

Co-Author Details :

Witness Name :	Harvey, Pat A. Date: 02/26/2007 13:07:04
Date_(GMT)	Signed by
2/26/2007 05:57	Name · Addock, Dave
	LIG-DIM WORH: DGADG#PSDIATDDDFCGA#P10#SGTDDGGADQQQQQQQQQ
	By entering your password you verify that you planned and/or executed
Justificatio	the work, directed the work, analyzed the result, or drew the conclusions described within this document.
	described within this document.
· · · · · · · · · · · · · · · · · · ·	
2/26/2007 06:07	:04 PM Name: Harvey, Pat A. Pre-Sig Hash: 73b0cadeclbdedf8234bdc64d8lae2e30laf8lba
	By entering your password you will be signing to say that you have
marifiancia	with a second the information contained in this dominant
commence of the control of the contr	ywewwexeyd
	Name:
<i>i</i>	Pre-Sig Hash:
Justificatio	n 🧎
f	Name:
	Pre-Sig Hash:
77	
Justificatio	
į	Nama:
	Pre-Sig Hash:
Justificatio	
Exchange Englisher Services (Services (Service	parameters and a
	Name:
	Pre-Sig Hash:
Justificatio	n i

. Information in this report is proprietary and should be handled according to DuPont Information Security policies

USING TEST FILE : 13-1 tot DAPE : 17/07/06 DATE

TEST DESCRIPTION DICC052-13-1

in action incided disc

SAMPLE ID : 13-1 SAMPLE THICKNESS: 3.030mm

Average sample temperature = 50 C Controller= 30 C

TU (C)	TG (C)	TL (C)	TH (C) TU-TL (C)	Q.:	RATIO
	। के कि के के का के कि कि हो। उसम			न्द्र हार्थ होने हार्य पान नेतृति तान तान भाग नाम होते. पा	ها خود سود. دره ایند دخت. سود نامه به بازد سید در در این سود.
50.0 50.6	48.2 48.0	40.4 40.8	30.0 19.64 29.5 19.75	9472 <u>1</u> 10096.7	0.211266 0.195657
60.6	48.1	40.9	29.5 19.73	10107.1	0.195166

Average sample temperature = 75 C Controller= 55 C

TU (C)	TG (C)	TL (C)	TH (C) T)-TL (C)	Q.	RATIO
78.1	65.9	58.4	49.3	19.74	8854.4	0.233231
85.2	72.0	65.6	54.7	19.63	10161.7	0.193207
85.2	72.0	65.6	54.7	19.62	10167.3	0.193013

_____ USING CALIBRATION FILE: ESLO4200 cal USING FIRST ORDER FIT

: 13-1.tst USING TEST FILE

SAMPLE ID : 3.030mm : 0.000e+000 SAMPLE THICKNESS

THE SAMPLE HAS A THERMAL CONDUCTIVITY OF: 3.651347e-001 W/mk = 0.365

AND A THERMAL RESISTANCE OF : 8.296308e-003 m2K/W : 50.78 C

AT A TEMPERATURE OF

THE DELTA T THROUGH THE SAMPLE IS : 19.79 C THE HEATER TEMPERATURE IS : 29.54 C : 31.10 C

THE DELTA T ACROSS THE STACK IS THE GUARD TEMPERATURE IS : 4810 C

THE EAMPLE HAS A THERMAL CONDUCTIVITY OF: 3.702624e-001 W/mk AND A THERMAL RESISTANCE OF 8.183385e-003 m2k/W AT A TEMPERATURE OF 75.40 C

THE DELTA T THROUGH THE SAMPLE IS : 19.62 C THE HEATER TEMPERATURE IS : 54,65 C THE DELTA T ACROSS THE STACK IS : 30.55 C : 72.02 C THE GUARD TEMPERATURE IS

OPPOR DuPont Electronic Laboratory Notebook

Identification Number : D100008 32.02

Experiment Name : D100008-18

Program Name : Zenite

Project Name: Thermal Conductivity

Document Name : ThermalConductivityofD100052-13-land13-2.pdf

Site Name : EXP ST

Business Unit : Engineering Polymers

Author Name : Adcock, Dave

Date: 02/26/2007 12:57:03

Co-Author Details :

Witness Name : Harvo	py, Pat A. Date: 02/26/2007 13:07:04					
Date (GMT)	Signed by					
2/26/2007 05·57·03 PM	Name: Addock, Dave					
1 2/26/2007 05:57:03 PM						
	By entering your password you verify that you planned and/or executed the work, analyzed the result, or drew the conclusions					
Justification .	described within this document.					
	Name: Harvey, Pat A.					
2/26/2007 06:07:04 PM	Pre-Sig Hash: 73b0cadeclbdedf8234bdc64d8lae2e30laf8lba					
	By entering your password you will be signing to say that you have					
dustification	witnessed the information contained in this document					
	Name :					
	Pre-Sig Hash:					
Justification						
	Name:					
	Pre-Sig Hash:					
Justification						
	1					
	Pre-Sig Hash:					
	FIC-SIG Maon.					
Justification						
Etimore-War inglister-ease at menyernen as it has a repair of the contract						
	Name:					
	Pre-Sig Hash:					
Justification						

. Information in this report is proprietary and should be handled according to DuPont Information Security policies

USING TEST FILE : 13-

TEST DESCRIPTION DICO052-13-1

infection meided disc

SAMPLE ID : 13-1 SAMPLE THICKNESS: 3.030mm

त्तर १८८ क्रिक्स सम्बद्ध विकास विकास विकास समिति कार्य का समिति हो है क्षेत्र समिति कार्य कार्य कार्य के किए क समिति कार्य कार्य कार्य के समिति कार्य के स्

Average sample temperature = 50 C Controller= 30 C

TU (C)	TG (C)	TL (C)	TH (C) TU-TL (C)	Q.	RATIO
50.0	48.2	40.4	30.0 19.64	9472 <u>1</u>	0.211266
60.6	48.0	40.8	29.5 19.75	10096.7	0.195657
60.6	48.1	40.9	29.5 19.73	10107.1	0.195166

Average sample temperature = 75 C Controller= 55 C

TU (C)	TG (C)	TL (C)	TH (C) T	U_TL (C)	Q	RATIO
78.1	65.9	58.4	49.3	19.74	8854.4	0.233231
85.2	72.0	65.6	54.7	19.63	10161.7	0.193207
85.2	72.0	65.6	54.7	19.62	10167.3	0.193013

USING FIRST ORDER FIT USING CALIBRATION FILE: ESLO4200 cal

: 13-1.tst USING TEST FILE

: 13-1 SAMPLE ID : 3.030mm SAMPLE THICKNESS

: 0.000e+000 CTE

THE SAMPLE HAS A THERMAL CONDUCTIVITY OF: 3.651347e-001 W/mK = 0.365 AND A THERMAL RESISTANCE OF: 8.298308e-003 m2K/W

- 50.78 C AT A TEMPERATURE OF

: 19.79 C THE DELTA T THROUGH THE SAMPLE IS : 29.54 C THE HEATER TEMPERATURE IS THE DELTA T ACROSS THE STACK IS : 31.10 C : 48.10 C THE GUARD TEMPERATURE IS

THE EAMPLE HAS A THERMAL CONDUCTIVITY OF: 3.7026248-001 W/mK AND A THERMAL RESISTANCE OF : 81838856-003 m2X/W

: 75.49 C AT A TEMPERATURE OF

: 19.62 C THE DELTA T THROUGH THE SAMPLE IS - 54.65 C THE HEATER TEMPERATURE IS

: 30.55 C : 72.02 C THE DELTA T ACROSS THE STACK IS THE GUARD TEMPERATURE IS